



Adhesive Backed Materials Ltd

ABM, Geith Ind Est, Crown Business Park, Tredegar, Gwent, UK. NP22 4EF

www.abmuk.net

info@abmuk.net

+44 (0) 1495 711895

Pakcel Data Sheet

Material Composition

No.	Component	Percentage
1	Dicumyl Peroxide	0.80%
2	Calcium Carbonate	20%
3	Zinc Oxide	1%
4	HST	1%
5	Stearic Acid	1%
6	Azodicarbonamide	3%
7	Ethylene Vinyl Acetate	65%
8	Polyethylene	1.10%
9	Master Batch	0.10%
10	Recycled Foam	7%

Physical Properties

Property	Value
Density	100-110 kg/m3
Shore Hardness "C"	40-45
Elongation at Break	Minimum > 130%
Tensile Strength	10 kgf/cm2
Operating Temperature Range	-40C to +80C

All information and recommendations about products are based on our existing knowledge and experience but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user is obliged to verify the above information before using the material.