



Adhesive Backed Materials Ltd

ABM, Geith Ind Est, Crown Business Park, Tredegar, Gwent, UK. NP22 4EF
www.abmuk.net info@abmuk.net +44 (0) 1495 711895

Butyl Rubber 65° shore Grade 147

Black High Temperature Butyl Rubber

Property	Detail
Material Type	Butyl rubber compound
Colour	Black
Hardness	65° Shore A (nominal)

Technical Data

Property	Test Method	Units	Typical Value
Specific Gravity	DIN 53508		1.20 ±0.05
Hardness	DIN 53505	Shore A	60 ±5
Tensile Strength	DIN 53504	kg/cm ²	90
Elongation at Break (min)	DIN 53504	%	350
Compression Set max (70°C/24hr/25% set)	DIN 53517	%	40
Tear Resistance - Angular (min)	DIN 53515	kg/cm	25
Polymer Content (Butyl)		%	100
Heat Ageing (72hr at 70°C)	ASTM D573		
Hardness change (max)		pts	+3



Adhesive Backed Materials Ltd

ABM, Geith Ind Est, Crown Business Park, Tredegar, Gwent, UK. NP22 4EF
www.abmuk.net info@abmuk.net +44 (0) 1495 711895

Tensile Strength change		%	+10 / -10
Elongation at Break change		%	+10 / -10
Volume Swell (70°C/72hr)	ASTM D471		
IRM Oil No.1			Not Recommended
IRM Oil No.2			Not Recommended
IRM Oil No.3			Not Recommended
Chemical Resistance - Ozone	ASTM D1149		Excellent
Chemical Resistance - Dilute Acids & Bases			Excellent
Chemical Resistance - Concentrated Acids & Bases			Excellent
Chemical Resistance - Oils			Fair
Chemical Resistance - Solvents			Not Recommended
Temperature Range		°C	-40 to +125
Colour			Black

The above figures are average values and should be considered as guidelines not specifications. While reasonable care has been taken to ensure that this data is representative, we do not warrant or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability or completeness of the information. We recommend evaluation prior to use to ascertain the suitability of the material for the application.